

Chemlok® 459X Primer

Description

LORD Chemlok® 459X primer is designed for promoting adhesion to thermoplastic elastomers (TPE), thermoplastic polyolefins (TPO) and EPDM. Chemlok 459X primer is in xylene solvent, diluted for direct application.

Chemlok 459X primer can be used in conjunction with urethane and epoxy adhesives, as well as with a variety of double-sided tapes. It may also serve as a primer to enhance the adhesion of polyurethane coatings on cured EPDM and other difficult-to-bond elastomers.

Features and Benefits

Versatile – enhances adhesion to difficult-to-bond elastomers, increasing the adhesion of coatings, double-sided tape and adhesives.

Easy to Apply – low viscosity allows for easy application; no dilution necessary.

Application

Surface Preparation – Wipe surface to be primed with a suitable solvent, or wash with detergent and water, then rinse.

Mixing – No mixing is required before or during use.

Applying – Apply Chemlok 459X primer by brush, dip or spray method. For optimum adhesion, the dry film thickness of Chemlok 459X primer should be approximately 2.5 micron (0.1 mil).

Drying/Curing – Allow primer to air-dry for 30-60 minutes at room temperature with good air flow, or use an oven at 93-121°C (200-250°F) for 5-10 minutes. A heat cycle generally improves adhesion.

Cleanup – Use a dry cloth wipe to remove wet primer. Remove dried primer with xylene or a ketone-type solvent.

Shelf Life/Storage

Shelf life is six months from date of shipment when stored at 21-27°C (70-80°F) in original, unopened container.

Typical Properties*

Appearance	Amber Liquid
Viscosity, cps @ 25°C (77°F) Brookfield LVT Spindle 1, 60 rpm	~10
Density kg/m ³ (lb/gal)	850.0-880.0 (7.1-7.3)
Solids Content by Weight, %	2.7-4.1
Flash Point (Seta), °C (°F)	27 (81)
Solvents	Xylene

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Cautionary Information

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Chemlok and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

LORD Corporation World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

www.lord.com

For a listing of our worldwide locations, visit LORD.com.