

Chemlok® 481/Curative 44 Adhesive

Description

LORD Chemlok® 481/Curative 44 adhesive is a two-component adhesive system used to bond thermoplastic elastomers (TPEs) to metals during the injection molding process. This adhesive system can also be used to fabricate hose for cold and hot [54-65°C (130-150°F)] liquids.

Features and Benefits

Versatile – bonds a wide variety of thermoplastic elastomers to metal.

Easy to Apply – applies easily by spray, brush or dip methods.

Convenient – requires only a single coat for most applications. For harsh environments, apply Chemlok 205 primer prior to adhesive application.

Application

Surface Preparation – Remove grease, oil, fingerprints, dust, mold release agents, rust and other contaminants from the surfaces to be bonded. Wear chemical resistant gloves. Wipe the surfaces with a clean cloth soaked in a solvent such as acetone, Methyl Ethyl Ketone (MEK) or isopropyl alcohol. On metal surfaces, a suitable alkaline degreasing agent may be used. Rinse metals and allow the surfaces to thoroughly dry.

Mixing – Thoroughly stir Chemlok 481 adhesive. While stirring, add 10 parts Chemlok Curative 44 curing agent, by weight, to 100 parts Chemlok 481 adhesive. If Chemlok 481 adhesive appears thick and gel-like in consistency, heat adhesive to 49°C (120°F) to lower the viscosity before mixing.

Thoroughly mix the two-component adhesive system before using. Mixed working life is 24 hours.

Chemlok 481/Curative 44 adhesive system is normally used full strength for brush and dip applications. For spray application, dilute adhesive with toluene or xylene at a ratio of 2.5-3.0 parts solvent to 1 part adhesive, by volume. Add solvent while stirring Chemlok 481 adhesive to prevent shocking the resin.

Typical Properties*

	481	Curative 44
Appearance	Straw Yellow Liquid	Transparent Brown Liquid
Viscosity, cps	400-1500 @ 38°C (100°F)	< 10 (typical) @ 25°C (77°F)
Density		
kg/m ³	880.7-916.7	1010.0-1040.0
(lb/gal)	(7.35-7.65)	(8.4-8.7)
Solids Content by Weight, %	17-20	47-51.5
Flash Point (Seta), °C (°F)	5 (41)	29 (85)
Solvents	Toluene, Xylene, Acetone	Xylene

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Applying – Apply adhesive system by spray, brush or dip methods. The recommended dry film thicknesses of Chemlok 481/Curative 44 adhesive is 20-37.5 micron (0.8-1.5 mil) for insert bonding TPEs [6.4 mm (0.25 in) thick or more]. For thinner sections, less adhesive can be used. For smooth surfaces (e.g., plated metals) or where bond failures to the metal occur, use of Chemlok 205 primer is recommended.

Drying/Curing – Allow adhesive to air-dry for 60 minutes at room temperature or hot air-dry for 10-15 minutes at 65°C (150°F).

For maximum bond strengths, preheat the coated inserts to 93-149°C (200-300°F) prior to bonding. Use a warm mold or increase the temperature of the melt to help improve adhesion. For injecting onto rubber or thermoplastic surfaces (e.g., TPE electrical plug onto rubber or plastic coated wire), preheating may not be necessary.

If preheating is not an option, the molded part can be post-heated to enhance adhesion. After molding, allow at least 24 hours before testing the bonded parts.

Cleanup – Use solvents such as xylene to remove adhesive before heat is applied. Remove cured adhesive by mechanical blasting methods.

Shelf Life/Storage

Shelf life is one year from date of shipment when stored in a well ventilated area at 21-27°C (70-80°F) in original, unopened container.

Cautionary Information

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Chemlok and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

LORD Corporation World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

www.lord.com

For a listing of our worldwide locations, visit LORD.com.

©2012 LORD Corporation OD DS3203 (Rev.8 10/12)

LORD
AskUsHow™