

# Autoseal<sup>®</sup> 3463B Cross-linker

## Description

LORD Autoseal<sup>®</sup> 3463B cross-linker is used with Autoseal aqueous coatings to enhance performance of the cured system.

## Features and Benefits

**Environmentally Friendly** – provides low VOC for reduced emissions and improved environmental compliance.

**Easy to Use** – prepackaged kits include cross-linker and resin in the proper ratio.

**Convenient** – requires fewer processing steps as cross-linker does not need to be pre-diluted with water.

**Durable** – provides good stability in water; enhances solvent resistance of cured Autoseal coatings.

## Application

**Surface Preparation** – Refer to the appropriate Autoseal coating data sheet for specific surface preparation instructions.

**Mixing** – Prepare the Autoseal resin by following the mixing instructions outlined on the Autoseal coating data sheet. While mixing the resin, add Autoseal 3463B cross-linker at a ratio of 100:2.5 resin to cross-linker, by weight.

**Applying** – Refer to the appropriate Autoseal coating data sheet for specific application instructions.

**Curing** – Refer to the appropriate Autoseal coating data sheet for specific curing instructions. Typical cure conditions for Autoseal coatings mixed with Autoseal 3463B cross-linker range from 1-8 minutes cure time and 177-288°C (350-550°F) cure temperature. Exact curing conditions will vary depending on the extrusion line and application conditions. The profile surface temperature when exiting the cure oven should be between 171-182°C (340-360°F).

**Cleanup** – Use warm water, ketone or aromatic solvents to clean up equipment.

## Shelf Life/Storage

Shelf life is six months from date of shipment when stored in a well ventilated area at 21-27°C (70-80°F) in original, unopened container.

## Typical Properties\*

Appearance	Milky White Liquid
Density	
kg/m <sup>3</sup>	1006.5-1054.5
(lb/gal)	(8.4-8.8)
Solids Content by Weight, %	39-41

\*Data is typical and not to be used for specification purposes.

## Cautionary Information

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Autoseal and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

---

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide . . . Ask Us How.

### **LORD Corporation World Headquarters**

111 Lord Drive  
Cary, NC 27511-7923  
USA

**Customer Support Center** (in United States & Canada)  
+1 877 ASK LORD (275 5673)

[www.lord.com](http://www.lord.com)