

# Chemlok® 207LH Primer

## Description

LORD Chemlok® 207LH primer is a low Hazardous Air Pollutant (HAP) primer designed for use under Chemlok 6411LH covercoat adhesive to bond a wide variety of vulcanized and unvulcanized rubber compounds to metals and other rigid substrates. It is composed of a mixture of polymers, organic compounds and mineral fillers dissolved or dispersed in a low HAP organic solvent system.

## Features and Benefits

**Easy to Apply** – applies easily by brush, dip, spray or roll coat methods; suitable for existing production lines.

**Durable** – provides rubber tearing bonds and excellent environmental resistance when used in combination with Chemlok 6411LH covercoat adhesive.

**Identifiable Appearance** – provides a brilliant blue color for easy identification when used over phosphatized substrates.

**Environmentally Friendly** – contains low HAP content (2.4 lb HAP/gal solid or 3.88% HAP content).

**Environmentally Resistant** – provides excellent resistance to a wide range of environmental conditions including hot solutions of ethylene/propylene glycol and water.

## Application

**Surface Preparation** – Thoroughly clean metal surfaces prior to adhesive application. Remove protective oils, cutting oils and greases by solvent degreasing or alkaline cleaning. Remove rust, scale or oxide coatings by suitable chemical or mechanical cleaning methods.

- **Chemical Cleaning**

Chemical treatments are readily adapted to automated metal treatment and adhesive application lines. Chemical treatments are also used on metal parts that would be distorted by blast cleaning or where tight tolerances must be maintained. Phosphatizing is a commonly used chemical treatment for steel, while conversion coatings are commonly used for aluminum.

## Typical Properties\*

Appearance	Blue Liquid
Viscosity	
cps	50-800
Brookfield LVT Spindle 2, 30 rpm	
seconds	10-60
Zahn Cup #2	
Density	
kg/m <sup>3</sup>	874.7-946.6
(lb/gal)	(7.3-7.9)
Solids Content by Weight, %	18-22
Flash Point (Seta), °C (°F)	19 (67)
Solvents	Methyl Amyl Ketone (MAK), Methyl Propyl Ketone (MPK)

\*Data is typical and not to be used for specification purposes.

# LORD TECHNICAL DATA

- **Mechanical Cleaning**

Grit blasting is the most widely used method of mechanical cleaning. However machining, grinding or wire brushing can be used. Use steel grit to blast clean steel, cast iron and other ferrous metals. Use aluminum oxide, sand or other nonferrous grit to blast clean stainless steel, aluminum, brass, zinc and other nonferrous metals.

For further detailed information on surface preparation of specific substrates, refer to Chemlok Adhesives application guide. Handle clean metal surfaces with clean gloves to avoid contamination with skin oils.

Apply Chemlok 207LH primer to stainless steel, aluminum, brass or other nonferrous substrates within one-half hour after cleaning. For ferrous substrates such as steel, a slightly longer layover can be tolerated if no rust is formed.

**Mixing** – Thoroughly stir Chemlok 207LH primer before use, and agitate sufficiently during use to keep dispersed solids uniformly suspended. Use an air-driven or other explosion-proof mixer on the agitator contained in an agitator drum or on other smaller packages.

Chemlok 207LH primer is normally used full strength for brush, dip and roll coat applications. For spray application, dilute primer to a Zahn Cup #2 viscosity of 18-20 seconds. Chemlok 207LH primer may be diluted with a non-HAP, ketone-type solvents such as MPK or t-butyl acetate without adverse effects on handling and application. The diluent must be slowly added to the primer while stirring. Careful attention should be given to agitation since dilution will accelerate settling. Refer to the Chemlok Adhesives application guide for further information.

**Applying** – Apply Chemlok 207LH primer by brush, dip, roll coat, spray or any method that gives a uniform coating and avoids excessive runs or tears.

For optimum adhesion, the dry film thickness of Chemlok 207LH primer should be 5.1-10.2 micron (0.2-0.4 mil). When using Chemlok 207LH primer over grit blasted substrates, apply a dry film thickness at the high end of the range. For all other applications (i.e., swaging or smooth substrates), apply Chemlok 207LH primer at the low end of the film thickness range.

**Drying/Curing** – Thoroughly dry parts coated with Chemlok 207LH primer before applying the covercoat adhesive. It is best to use temperatures of 65-93°C (150- 200°F) and abundant dry circulating air; however, forced air drying is possible at temperatures up to 149°C (300°F) for short periods of time. Maximum air flow at minimum temperatures will give the best results. After parts have dried, apply Chemlok covercoat using similar application methods.

Dried films of Chemlok 207LH primer are non-tacky; therefore, coated parts can be piled into tote pans for subsequent processing. Wear clean gloves when handling coated parts and cover the tote pans to prevent contamination by dirt, dust, grease, oil, etc. If properly protected, coated parts can be stored for several weeks before applying covercoat or bonding.

**Cleanup** – Clean areas with a rag as soon as possible using MPK, MAK or methyl ethyl ketone (MEK).

# LORD TECHNICAL DATA

## **Shelf Life/Storage**

Shelf life is six months from date of shipment when stored at 21-27°C (70-80°F) in original, unopened container.

## **Cautionary Information**

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Chemlok and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

---

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

**LORD Corporation**  
**World Headquarters**

111 Lord Drive  
Cary, NC 27511-7923  
USA

**Customer Support Center** (in United States & Canada)

+1 877 ASK LORD (275 5673)

[www.lord.com](http://www.lord.com)

For a listing of our worldwide locations, visit [LORD.com](http://LORD.com).